

## Milmar Silver Perm

### **PRODUCT DESCRIPTION**

**Face Material:** Polyester films, top coated for ink receptivity: **MILMAR T.C. 25 μm :** Bright Silver or Dull Silver

Adhesive: Permanent high-performance, acrylic based.

**Liner:** Mercury. Bleached Kraft paper, ca. 160 gr/sqm, two-side polyethylene coated, without breaklines and backprinting.

Backing with excellent dimensional stability.

#### **TYPICAL USE**

Milmar Silver films : luxury labels for household or industrial appliances, audio and video equipment, calculators, nameplates, toys, panels for decorative purposes, luxury packaging for perfumery or jewellery.

**GENERAL REMARK : factors affecting adhesion** 

Adhesion failure problems can be avoided by :

• Where possible, always test the proposed construction under actual application and end-use conditions because a 100 % multi-purpose adhesive for all substrates does not exist.

• Being familiar with factors which adversely affect adhesion :

- Labels or stickers should not be applied onto dusty, dirty, oily or oxidized surfaces.
- Mould release agents on blow-moulded plastic surfaces inhibit adhesion.
- Adhesion failure may occur on substrates with low surface tension, such as polyethylene or polypropylene. Rubber based adhesives stick better to low energy surfaces than acrylics.
- Avoid the use of relatively rigid facestocks on highly curved or small diameter surfaces.
- Do not use pressure-sensitive materials outside the recommended service temperature range, or do not apply below the minimum application temperature.

#### PROCESSING

The special topcoating allows printing solvent based by screen printing. For letterpress and offset printing, please contact your ink supplier. We recommend to maintain an unprinted area of 3-4 mm on the edges of the printed decal to avoid edge lifting.

#### SHELF LIFE

2 years stored at 50  $\pm$  10 % RH at 15 - 25°C  $\,$  in its original packaging.

# PHYSICAL PROPERTIES (TYPICAL VALUES)

	Ave	rage Values	Test Method
Thickness (micro	n)		
Film + Adhesive	50		ISO 534
Adhesive data, 23	°C		
Peel adhesion 180	° on gl	ass	
- 20 min. residence (N/25 mm)		11	FTM1
- 24 hour residence (N/25 mm)		14	FTM1
Quick Tack (N)		16	FTM9
Dimensional stab	ility		
Shrinkage (1 week at 70°C applied on Aluminium)	no shrinkage		FTM14
Temperature rang	ges		
Application (°C)	+10		Minimum
End-use (°C)	-20 to +130		
Toy labelling	in compliance with EN 71/3		
Solvent and chem	nical re	esistance	
Solvent Resistance	Resistant to most oils, greases, aliphatic solvents, alcohols.		
Petrol Resistance	Resistant to short limited contacts. If extended contact, edge-lifting will occur.		
Chemical Resistance	Resistant to most mild acids, mild alkalis.		

#### EXPECTED DURABILITY

The expected vertical outdoor durability of the unprocessed product in central Europe (Zone 1) is up to: 2 years.



This information is based on successful real life experience and artificial aging according to ISO 4892-2. Middle European exposure conditions, vertical exposure. Exposure to severe humidity, ultra-violet light or conditions found in tropical, subtropical or desert regions will cause more rapid deterioration than under conditions existing in "normal" temperate climates.

#### DISCLAIMER

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see

http://terms.europe.averydennison.com. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

